



EDILPOL

Rev. 1 del 01/07/2013

DESCRIPTION	<p>EDILPOL is a plastomeric modified bitumen waterproofing membrane (APP), industrially manufactured by impregnation of the reinforcement with the waterproofing compound based on distilled bitumen modified with polyolefin polymers, which gives to the compound excellent technical characteristics.</p> <p>The composite reinforcement, made of nonwoven polyester in combination with fiberglass, conveys good mechanical characteristics, excellent dimensional stability and elastic performance. Shaping of sheets, straightness, dimensional and surface uniformity are accomplished by hot calendaring of the mass at hot melt fluid state.</p> <p>The upper surface is coated with anti-adhesive amorphous sand. The lower surface is coated with a thermo-fusibile polyolefin film.</p>
FIELD OF APPLICATION	<p>EDILPOL is suitable as under layer or as intermediate layer in multi-layer waterproofing systems, with compatible membranes.</p> <p>General roofing, on or under floors, wall constructions, are valid examples of the design application of this product. It is not suitable for roof gardens.</p> <p>It can be applied onto every substrate and it is suitable for any climate conditions and all the situations where a barrier against water is required.</p>
METHOD OF INSTALLATION	<p>The excellent thermoplastic properties of the waterproofing compound allow the application with torch-on system or hot air generator. In particular situations, it could be applied with appropriate sealants or mechanical fastenings.</p> <p>The application of the membrane must be carried in good weather conditions and after the substrate has been adequately cleaned and prepared.</p>
PACKING AND STORAGE	<p>The product is packed as standing rolls on wooden pallets wrapped with thermoshinking protective hoods. Rolls must be stored in the upright position, without stacking the pallets to avoid deformations which can compromise the correct application of the membrane. The product must be stored indoor, protected from heat and frost.</p>
SPECIAL INDICATIONS	<p>SAFETY INFORMATION</p> <p>The product does not contain dangerous substances and can be considered as household rubbish or industrial waste (identification code EWC170302).</p>
INTENDED USE OR USES	<p>Flexible sheets for waterproofing. Reinforced bitumen sheets for roof waterproofing</p> <p>Flexible sheets for waterproofing. Bitumen damp proof sheets including bitumen basement tanking sheets</p>

1. Anti-adhesive surface
2. Waterproofing mass
3. Reinforcement
4. Waterproofing mass
5. Torch-off film



EDILPOL

Rev. 1 del 01/07/2013

TECHNICAL DATA

	Norm	Value	Unit	Tolerance
Thickness	EN1849-1:1999	3-4	(mm)	±0,2
Weight	EN1849-1:1999	3	(kg/m ²)	±10%
Roll length	EN1848-1:1999	10	(m)	-1%
Roll width	EN1848-1:1999	1	(m)	-1%
Straightness	EN1848-1:1999	PASSED	-	20 mm / 10 m
Flexibility at low temperature (pliability)	EN1109:2013	-5	(°C)	≤
Heat flow resistance	EN1110:2010	120	(°C)	≥
Watertightness	EN1928-B:2000	100	(kPa)	≥
Water vapour transmission properties	EN1931:2000	20.000	(μ)	-
M.d. C.d.				
Tensile properties: maximum tensile strength	EN12311-1:1999	500 / 350	(N/50 mm)	-20%
Tensile properties: elongation at break	EN12311-1:1999	40 / 40	(%)	-15
Resistance to tearing (nail shank)	EN12310-1:1999	150 / 150	(N)	-30%
Dimensional stability	EN1107-1:1999	±0,3 / ±0,3	(%)	≤
Shear resistance of joints	EN12317-1:1999	500 / 350	(N/50 mm)	-20%
Resistance to static puncture	EN12730-A:2015	NPD		
Resistance to impact	EN12691-A:2006	NPD		
External fire performance (note 1)	EN1187:2012/EN13501-5:2005+A1:2009	Froof	Class	-
Reaction to fire	EN11925-2:2010/EN13501-1:2007+A1:2009	F	Class	-
Root resistance	EN13948:2007	NPD		
Visible defects	EN1850-1:2001	PASSED	-	-
Durability: Flexibility at low temperature after artificial ageing	EN1296:2000/EN1109:2013	NPD		
Durability: Flow resistance at elevated temperature after artificial ageing	EN1296:2000/EN1110:2010	110	(°C)	-10
Durability: Watertightness after artificial ageing	EN1296:2000/EN1928-B:2000	PASSED	(kPa)	≥ 60
Durability: Visual defects after artificial ageing	EN1297:2004/EN1850-1:1999	PASSED	-	PASSED
Durability: Watertightness against chemicals	EN1296:2000/EN1847:2009	NPD		

NORMS AND CERTIFICATIONS

EN13707; EN13969 - 1381 - 1381-CPR-415



Substates or
intermediate
layers



Damp proof
courses



Foundations