

SOPRAFIX HP

SOPRAFIX HP is a flexible SBS elastomeric bitumen waterproofing membrane with a composite polyester/glass reinforcement, to be mechanically fastened under the method of **SOPRAFIX Bicouche**. The topside is covered by a thermofusible film and the underside is covered with fine sand.

The lineage of the fasteners axis on the overlap is 5 cm from the edge.

User application

SOPRAFIX HP is mainly used as first layer mechanically fastened for bilayer self-protected systems.

SOPRAFIX HP is intended to be laid on all bearing elements accepting mechanical fasteners. It can be used in new construction or renovation.

All the applications are described in Technical Approvals or **SOPREMA**'s Technical Guidelines in force.

Composition

SOPRAFIX HP	
Reinforcement	Composite polyester / glass
Binder	Elastomeric bitumen : blend of selected bitumen and SBS* thermoplastic polymers
Thickness Minimum on overlap	2,6 mm (- 5 %; + 5%)
Topside	Thermofusible film
Underside	Fine sand
Overlap	Double at 5 and 10 cm from edge
*According to UEAtc directives concerning the normalization of waterproof elastomeric SBS bitumen coverings.	

Packaging

SOPRAFIX HP		
Dimensions of the roll	Standard* 7 m x 1 m	Export 10 m x 1 m
Weight of the roll	about 25 kg	about 32 kg
Storage	Upright on pallet with plastic wrapping, protected against moisture	
Roll lengths are given with a tolerance of $\leq 1\%$. Roll can be cut in two parts. In this case, the shortest length is 2 meters and the total length is equal to the nominal length. Width of roll is given with a tolerance of 1% (UEAtc). Rolls must be stored upright on flat ground. Pallets may be stacked to a maximum of two high with separating layer. During storage, protect the rolls against moisture. In cold weather, we recommend that the rolls be kept at a minimum temperature of + 2°C (+ 36 °F) for at least 5 hours before installation.		

*Prevents from the arduousness for roofers on worksite

Characteristics (outside CE marking)

	SOPRAFIX HP
Static puncture resistance (NF P 84-352)	
- with SOPRAFIX AR (or ELASTOPHENE FLAM 25 AR)	≥ 15 kg (L3)
- with SOPRALENE FLAM 180 AR	≥ 25 kg (L4)
Dynamic puncture resistance (NF P 84-353)	
- with SOPRAFIX AR (or ELASTOPHENE FLAM 25 AR)	≥ 20 J (D3)
- with SOPRALENE FLAM 180 AR	≥ 20 J (D3)

Installation

In Technical Approval **SOPRAFIX Bicouche**, **SOPRAFIX HP** is semi-loose laid by unrolling the membrane and mechanically fastened on the overlaps. All the joints are welded.

SOPRAFIX HP requires a second layer of self-protected elastomeric waterproofing.

All the applications are described in Technical Guidelines or Technical Approvals in force.

Special indications

Hygiene, health and environment:

The product does not contain any substance likely to be detrimental to health or to environment and complies with generally admitted Health and Safety Requirements. For further information, please refer to relevant Safety Data Sheet.

Traceability:


Product traceability is ensured through a manufacturing code present on the packaging.

Quality control:

SOPREMA has always attached the highest importance to the quality of its products, to the respect of environment and men.

For this reason, we apply an integrated management of the Quality and Environment certified **ISO 9001** and **ISO 14001**.

CE marking

 1119 SOPRAFIX HP
SOPREMA 14 rue de Saint-Nazaire – CS 60121 67025 STRASBOURG cedex 06 Construction Product Regulation (CPR) Declaration of Performance : DoP n° WPBFR221 Certificate of Factory Production Control : 1119-CPR-13132, 13133, 13134.
<p style="text-align: center;">EN 13707</p> <p>Membrane composed of modified elastomeric bitumen and a composite polyester/glass reinforcement. Topside is covered with a thermofusible film and the underside is covered with fine sand. Dimensions 7 m or 10 m x 1 m x 2,6 mm. Underlayer mechanically fastened, overlap welded.</p>

Essential characteristics	Performances	Harmonised Technical Specification
Classification for external fire exposure (Note 1)	F_{ROOF} (t1,t2,t3,t4)	EN 13707:2004 + A2:2009
Reaction to fire	E	
Watertightness	Conform	
Tensile properties : Tensile strength L x T (N / 50 mm) Elongation L x T (%)	≥ 450 x 300 20 x 20	
Root resistance	NPD	
Resistance to static loading (kg)	15	
Resistance to impact (mm)	600	
Resistance to tearing (N)	≥ 150	
Joint strength Peel resistance of joints (N / 50 mm) Shear resistance of joints (N / 50 mm)	NPD NPD	
Durability Flow resistance at elevated temperature after ageing	90°C	
Flexibility at low temperature	-16°C	
Dangerous substances (Notes 2 and 3)	Complies	

Note 1 : Since external fire performance depends on the other components of the roof build-up, no performance can be given.

Note 2 : This product does not contain asbestos or tar constituents.

Note 3 : Since there is no European test method available, no performance declaration for leaching behavior can be made. It must be made according to national rules in force in the place of use.

Additional characteristics	SOPRAFIX HP
	MLV*
Flow resistance at elevated temperature (EN 1110)	100 °C
Dimensional stability (EN 1107-1)	0,4 %
*MLV = Manufacturer's Limiting Value: Minimum or maximum value as started by the manufacturer to be met during testing of type, internal quality control or external supervision with a confidence level of 95 %	